

Technical Data Sheet - KERABIT TORCH-ON BITUMEN DAMP PROOF COURSE



Kerabit Oy
Puistokatu 25-27, 08150 Lohja, Finland
06
006.CPR.SKPH

Kerabit
Tuotteet

Bitumen damp proof courses EN 14967:2007

Product description	
Use	Bitumen damp proof course
Application	Bonding onto the substrate by melting the undersurface of the membrane and the protective film with a blowtorch. Applying with mechanical fastening, when necessary
Reinforcement	Reinforced polyester
Coating	SBS modified bitumen
Surfacing	Sand or slate and/or mineral granules
Bottom surfacing	Thermofusible film and torch-on elastomer bitumen

Characteristic	Method	Unit	Nominal value	minimum	maximum
Length	EN 1848-1	m	8	-	-
Width	EN 1848-1	m	0,5	0,495	0,505
Width	EN 1848-1	m	0,33	0,325	0,335
Width	EN 1848-1	m	0,3	0,295	0,305
Width	EN 1848-1	m	0,2	0,195	0,205
Slate/mineral granules:					
Mass per unit area	EN 1849-1	g/m ²	5000	4750	-
Nominal thickness	EN 1849-1	mm	4,4	4,1	4,7
Sand:					
Mass per unit area	EN 1849-1	g/m ²	4000	3800	-
Nominal thickness s	EN 1849-1	mm	3,3	3,1	3,7
Straightness	EN 1848-1	mm / m	pass		16/8
Visual defects	EN 1850-1	-		no defects	
Declaration of performance	006.CPR.SKPH				
AVCP- class	3				
Certificate of factory production control	0809-CPR-1030				

Fire properties	Method	Classification	Fireclass
Reaction to fire	EN ISO 11925-2	EN 13501-1	NPD
External fire performance	ENV 1187 ¹⁾	EN 13501-5	B _{ROOF} (t2)

Characteristic	Method	Unit	Nominal value	minimum	maximum
Watertightness	EN 1928 B	kPa	pass	300	
Resistance to impact	EN 12691	mm	1000	800	
Nail shank tear resistance	EN 12310-1				
- in longitudinal direction		N	250	150	350
- in transverse direction	N	350	200	500	
Watertightness after ageing	EN 1296/ EN 1928	kPa	pass	>2	
Chemical resistance	EN 1847/ EN 1928	kPa	NPD		
Pliability	EN 1109				
- surface		°C	-20	-20	
- bottom	°C	-20	-10		

Dangerous substances^{2),3)} No dangerous substances

1) see: www.kerabit.fi
 2) No asbestos or coal tar constituents
 3) In the absence of European harmonized test methods, verification and declaration on release/content has to be done taking into account national provisions in the place of use

NPD = no performance determined