

Technical Data Sheet - KERABIT 3700 UT FLEECE



0809 ¹⁾

Kerabit Oy
Puistokatu 25-27, 08150 Lohja, Finland
18
004.CPR.55510

Kerabit
Tuotteet

Reinforced bitumen sheets for roof waterproofing EN 13707	Underlay for discontinuous roofing 13859-1
Bitumen damp proof sheets including basement tanking sheet EN 13969	Bitumen vapour control layers EN 13970

Product description	
Use	Base sheet in built-up roofing, bitumen damp proof sheet, underlay for discontinuous roofing, bitumen vapour control layer
Application	Bonding onto the substrate by melting the undersurface of the membrane and the protective film with a blowtorch. Applying with mechanical fastening, when necessary
Reinforcement	Reinforced polyester
Coating	SBS modified bitumen
Surfacing	PP non-woven fabric
Bottom surfacing	Thermofusible film and torch-on elastomer bitumen

Characteristic	Method	Unit	Nominal value	minimum	maximum
Length	EN 1848-1	m	7	-	-
Width	EN 1848-1	m	1	0,995	1,005
Straightness	EN 1848-1	mm / m	pass		14/7
Mass per unit area	EN 1849-1	g/m ²	3700	3515	-
Nominal thickness	EN 1849-1	mm	2,6	2,4	3,0
Visual defects	EN 1850-1	-	no defects		
Declaration of performance	004.CPR.55510				
AVCP- class			2+	3	
Certificate of factory production control	0809-CPR-1030				

Fire properties	Method	Classification	Fireclass				
Reaction to fire	EN ISO 11925-2	EN 13501-1	NPD				
External fire performance	ENV 1187 ²⁾	EN 13501-5	B _{ROOF} (t2)				

Characteristic	Method	Unit	EN 13707	EN 13969	EN 13970	EN 13859-1	minimum	maximum
Watertightness	EN 1928 B	kPa	pass	pass	pass		300	
	EN 1928 A	mm				W1	200	
Tensile strength - in longitudinal direction - in transverse direction	EN 12311-1	N/ 50 mm	750	750	750	750	600	900
		N/ 50 mm	550	550	550	550	400	700
Elongation	EN 12311-1	%	40	40	40	40	25	55
Nail shank tear resistance - in longitudinal direction - in transverse direction	EN 12310-1	N	250	250	250	250	150	350
		N	300	300	300	300	150	450
Resistance to static loading	EN 12370 A	kg	15				15	
	EN 12370 B	kg		NPD		NPD		
Resistance to impact**	EN 12691	mm	1500/900	1500/900	1500/900	1500/900	1000	
Durability*								
* Water vapor transmission	EN 1296/1931	m						
* Watertightness	EN 1928 B/A	kPa/mm		pass		W1	60/200	
Tensile strength - in longitudinal direction - in transverse direction	EN 12311-1	N/ 50 mm				400	320	480
		N/ 50 mm				300	220	380
Elongation	EN 12311-1	%				30	20	40
*Chemical resistance	EN 1847/1928 EN 1847/1931			NPD				
* Pliability: surface bottom	EN 1296/1109	°C	-15				-10	
		°C	-10				0	
* Flow resistance at elevated temperature : surface bottom	EN 1296/1110	°C					80	
			80				80	
Pliability : surface bottom	EN 1109	°C	-20	-20			-20	
			-20	-20			-10	
Water vapor resistance	EN 1931	m ² sPa/kg			2,2 x 10 ¹²		2 x 10 ¹²	
Flow resistance at elevated temperature	EN 1110	°C	80	80	80	80	80	
Dimensional Stability	EN 1107-2	%	0,3	0,3	0,3	0,3		0,6
Dangerous substances ^{3),4)}			No dangerous substances					

1) concerns only attestation of conformity system 2+, 2) see: www.kerabit.fi
3) No asbestos or coal tar constituents , 4) In the absence of European harmonized test methods,
verification and declaration on release/content has to be done taking into account national provisions in
the place of use

NPD = no performance determined
*tested after ageing
** testing point bitumen/sand
V3 6/23