

## Technical Data Sheet - KERABIT Titan



**Nordic Waterproofing Oy**  
Puistokatu 25-27, 08150 Lohja, Finland  
**19**  
001.CPR.Titan



Reinforced bitumen sheets for roof waterproofing EN 13707

Product description					
Use	Top sheet with adhesive edges 1:2- 1:20 (2,86°- 26,6°) 1:15- 1:20 underlay membrane must be used				
Application	Mechanical fastening with adhesive edges				
Reinforcement	Reinforced polyester				
Coating	SBS modified bitumen				
Surfacing	Slate and/or mineral granules				
Bottom surfacing	Sand				
Characteristic	Method	Unit	Nominal value	minimum	maximum
Length	EN 1848-1	m	8	-	-
Width	EN 1848-1	m	1	0,995	1,005
Mass per unit area	black	EN 1849-1	g/m <sup>2</sup>	4400	4180
	basic color				
Nominal thickness	EN 1849-1	mm	3,4	3,1	3,7
Straightness	EN 1848-1	mm / m	pass		16/8
Visual defects	EN 1850-1	-		no defects	
Declaration of performance	001.CPR.Titan				
AVCP- class	2+				
Certificate of factory production control	0809-CPR-1030				
Fire properties	Method	Classification	Fireclass		
Reaction to fire	EN ISO 11925-2	EN 13501-1	NPD		
External fire performance	ENV 1187 <sup>1)</sup>	EN 13501-5	B <sub>ROOF</sub> (t2)		
Characteristic	Method	Unit	Nominal value	minimum	maximum
Watertightness	EN 1928 B	kPa	pass	300	
Tensile strength	EN 12311-1	N/ 50 mm	750	600	900
		N/ 50 mm	550	400	700
Elongation	EN 12311-1	%	40	25	55
		%	40	25	55
Nail shank tear resistance	EN 12310-1	N	230	150	310
		N	230	150	310
Peel resistance of joints	EN 12316-1	N/ 50 mm	NPD		
Shear resistance of joints	EN 12317-1	N/ 50 mm	NPD		
Resistance to static loading	EN 12370 A	kg	15	15	
Resistance to impact	EN 12691	mm	1250	1000	
Pliability	EN 1109	°C	-25	-25	
Pliability after ageing	EN 1296/1109	°C	-15	-15	
Adhesion of granules	EN 12039	%	8	0	30
Flow resistance at elevated temperature	EN 1110	°C	80	80	
Flow resistance at elevated temperature after ageing	EN 12961110	°C	80	80	
Dimensional Stability	EN 1107-2	%	0,3		0,6
Dangerous substances <sup>2),3)</sup>	No dangerous substances				
1) see: <a href="http://www.kerabit.fi">www.kerabit.fi</a>			NPD = no performance determined		
2) No asbestos or coal tar constituents					
3) In the absence of European harmonized test methods, verification and declaration on release/content has to be done taking into account national provisions in the place of use					