

Technical Data Sheet - KERABIT 2500 U



Nordic Waterproofing Oy
Puistokatu 25- 27, 08150 Lohja, Finland
06
005.CPR.15520



Reinforced bitumen sheets for roof waterproofing EN 13707 Bitumen vapour control layers EN 13970
Underlay for discontinuous roofing 13859-1

Product description	
Use	Base sheet in built-up roofing, bitumen damp proof sheet, bitumen vapour control layer
Application	Mechanical fastening and/or pour and roll applying depending on intended use and substrate
Reinforcement	Polyester
Coating	SBS modified bitumen
Surfacing/ Bottom surfacing	Sand/ Sand

Characteristic	Method	Unit	Nominal value	minimum	maximum
Length	EN 1848-1	m	15	-	-
Width	EN 1848-1	m	1	0,995	1,005
Straightness	EN 1848-1	mm / m	pass		30/15
Mass per unit area	EN 1849-1	g/m ²	2500	2375	-
Nominal thickness	EN 1849-1	mm	2,2	2,0	2,4
Visual defects	EN 1850-1	-	no defects		

Declaration of performance	005.CPR.15520	
AVCP- class	2+	3
Certificate of factory production control	0809-CPR-1030	-

Fire properties	Method	Classification	Fireclass				
Reaction to fire	EN ISO 11925-2	EN 13501-1	NPD				
External fire performance	ENV 11872 ²⁾	EN 13501-5	B _{ROOF} (t2)				

Characteristic	Method	Unit	EN 13707	EN 13970	EN 13859-1	minimum	maximum
Watertightness	EN 1928 B	kPa	pass	pass		300	
	EN 1928 A	mm			W1	200	
Tensile strength - in longitudinal direction - in transverse direction	EN 12311-1	N/ 50 mm	600	600	600	400	800
		N/ 50 mm	400	400	400	300	500
Elongation	EN 12311-1	%	35	35	35	20	50
Nail shank tear resistance - in longitudinal direction - in transverse direction	EN 12310-1	N	150	150	150	130	170
		N	250	250	250	130	300
Resistance to static loading	EN 12370 A	kg	20			15	
Resistance to impact	EN 12691	mm	1000	1000	1000	800	
Durability:*							
* Water vapor resistance	EN 1296/1931	m		NPD			
* Watertightness	EN 1928 B	kPa			W1	200	
*Tensile strength - in longitudinal direction - in transverse direction	EN 12311-1	N/ 50 mm			400	320	480
		N/ 50 mm			320	240	400
*Elongation	EN 12311-1	%			30	20	45
* Chemical resistance	EN 1847/1931			NPD			
* Pliability	EN 1296/1109	°C	-20			-10	
* Flow resistance at elevated temperature	EN 1296/1110	°C	80	80	80	80	
Pliability	EN 1109	°C	-25	-25	-25	-20	
Water vapor resistance	EN 1931	m ² sPa/kg			1,5 x 10 ¹²	1 x 10 ¹²	
Flow resistance at elevated temperature	EN 1110	°C	80	80	80	80	
Dimensional Stability	EN 1107-2	%	0,3	0,3	0,3		0,6

Dangerous substances^{3), 4)} No dangerous substances

1) concerns only attestation of conformity system 2+
2) see: www.kerabit.fi
3) No asbestos or coal tar constituents
4) In the absence of European harmonized test methods, verification and declaration on release/content has to be done taking into account national provisions in the place of use

NPD = no performance determined
*after ageing

V8 4/21