

# Technical Data Sheet - KERABIT Titan Nature



Nordic Waterproofing Oy  
Puistokatu 25-27, 08150 Lohja, Finland  
20  
001.CPR.Titan Nature



Reinforced bitumen sheets for roof waterproofing EN 13707

## Product description

Use	Top sheet with adhesive edges 1:2- 1:20 (2,86°- 26,6°) 1:15- 1:20 underlay membrane must be used
Application	Mechanical fastening with adhesive edges
Reinforcement	Reinforced polyester
Coating	SBS modified bitumen + tall oil
Surfacing	Black mineral granules
Bottom surfacing	Sand

Characteristic	Method	Unit	Nominal value	minimum	maximum
Length	EN 1848-1	m	8	-	-
Width	EN 1848-1	m	1	0,995	1,005
Mass per unit area	EN 1849-1	g/m <sup>2</sup>	4400	4180	-
Nominal thickness	EN 1849-1	mm	3,4	3,1	3,7
Straightness	EN 1848-1	mm / m	pass		16/8
Visual defects	EN 1850-1	-	no defects		

Declaration of performance

001.CPR.Titan Nature

AVCP- class

2+

Certificate of factory production control

0809-CPR-1030

## Fire properties

### Method

### Classification

### Fireclass

Reaction to fire	EN ISO 11925-2	EN 13501-1	NPD		
External fire performance	ENV 1187 <sup>1)</sup>	EN 13501-5	B <sub>ROOF</sub> (t2)		

Characteristic	Method	Unit	Nominal value	minimum	maximum
Watertightness	EN 1928 B	kPa	pass	300	
Tensile strength	EN 12311-1	N/ 50 mm	750	600	900
- in longitudinal direction					
- in transverse direction		N/ 50 mm	550	400	700
Elongation	EN 12311-1	%	40	25	55
- in longitudinal direction					
- in transverse direction			40	25	55
Nail shank tear resistance	EN 12310-1	N	230	150	310
- in longitudinal direction					
- in transverse direction		N	230	150	310
Peel resistance of joints	EN 12316-1	N/ 50 mm	NPD		
Shear resistance of joints	EN 12317-1	N/ 50 mm	NPD		
Resistance to static loading	EN 12370 A	kg	15	15	
Resistance to impact	EN 12691	mm	1250	1000	
Pliability	EN 1109	°C	-25	-25	
Pliability after ageing	EN 1296/1109	°C	-15	-15	
Adhesion of granules	EN 12039	%	8	0	30
Flow resistance at elevated temperature	EN 1110	°C	80	80	
Flow resistance at elevated temperature after ageing	EN 12961110	°C	80	80	
Dimensional Stability	EN 1107-2	%	0,3		0,6

Dangerous substances<sup>2),3)</sup>

No dangerous substances

1) see: [www.kerabit.fi](http://www.kerabit.fi)

NPD = no performance determined

2) No asbestos or coal tar constituents

3) In the absence of European harmonized test methods, verification and declaration on release/content has to be done taking into account national provisions in the place of use