

Technical Data Sheet - KERABIT 5000 TOP FR



Kerabit Oy
Puistokatu 25-27, 08150 Lohja, Finland
22
002.CPR.15555

Kerabit
Tuotteet

Reinforced bitumen sheets for roof waterproofing EN 13707

Product description	
Use	Cap sheet in built-up roofing (TL2) ⁴⁾
Application	Bonding onto the substrate by melting the undersurface of the membrane and the protective film with a blowtorch. Applying with mechanical fastening, when necessary
Reinforcement	Reinforced polyester ($\geq 220 \text{ g/m}^2$)
Coating	SBS modified bitumen
Surfacing	Slate and/or mineral granules
Bottom surfacing	Thermofusible film and torch-on elastomer bitumen

Characteristic	Method	Unit	Nominal value	minimum	maximum	
Length	EN 1848-1	m	8	-	-	
Width	EN 1848-1	m	1	0,995	1,005	
Mass per unit area	basic colors black	EN 1849-1	g/m ²	5000	4750	-
				5400	5130	-
Nominal thickness	EN 1849-1	mm	4,4	4,1	4,7	
Straightness	EN 1848-1	mm / m	pass		16/8	
Visual defects	EN 1850-1	-	no defects			
Declaration of performance				002.CPR.15555		
AVCP- class				2+		
Certificate of factory production control				0809-CPR-1030		

Fire properties	Method	Classification	Fireclass
Reaction to fire	EN ISO 11925-2	EN 13501-1	E
External fire performance	ENV 1187 ¹⁾	EN 13501-5	B _{ROOF} (t2)

Characteristic	Method	Unit	Nominal value	minimum	maximum
Watertightness	EN 1928 B	kPa	pass	300	
Tensile strength	EN 12311-1				
		- in longitudinal direction	N/ 50 mm	650	600
- in transverse direction		N/ 50 mm	550	400	700
Elongation	EN 12311-1				
		- in longitudinal direction	%	40	25
- in transverse direction		%	40	25	55
Nail shank tear resistance	EN 12310-1				
		- in longitudinal direction	N	250	150
- in transverse direction		N	300	150	450
Resistance to static loading	EN 12370 A	kg	NPD		
Resistance to impact	EN 12691	mm	1000	800	
Pliability: surface	EN 1109				
		bottom	°C	-20	-20
		°C	-20	-10	-25
Pliability after ageing: surface	EN 1296/1109				
		bottom	°C	-15	-10
		°C	-10	0	
Adhesion of granules	EN 12039	%	8	0	30
Flow resistance at elevated temperature : surface	EN 1110				
		bottom	°C	80	80
		°C	80	80	95
Flow resistance at elevated temperature after ageing	EN 12961110	°C	80	80	
Dimensional Stability	EN 1107-2	%	0,3		0,6

Dangerous substances^{2),3)} No dangerous substances

1) see: www.kerabit.fi
 2) No asbestos or coal tar constituents
 3) In the absence of European harmonized test methods, verification and declaration on release/content has to be done taking into account national provisions in the place of use
 4) Product class requirements for modified bitumen membranes by Finnish Roofing Association
 NPD = no performance determined