

Kerabit

Kerabit KBL 20/100

Päivitetty 25.4.2023 Tulostettu 10.6.2026

Kerabit KBL 20/100 Modified Bitumen Primer is a cold-applied, nicely spreading, quick-drying modified bitumen solution containing adhesion improving agents.

Kerabit KBL 20/100 forms an excellent underlay for an isolation layer made of Kerabit KB 100/50 modified bitumen or of torch-applied modified bitumen membranes. For adhesive application on demanding substrates (concrete and metal surfaces) when modified bitumen or torch-applied modified bitumen membranes are used. Mix before use.

The product is not for use indoors.



Technical data

Manufacturer / Manufactured for	Kerabit Oy, Lohja plant
Country of origin	Denmark
Drying time	2 - 3 hours at +20 °C
Need for materials	0,1 - 0,3 l / m ²
Container Size	20 l

Additional information

Applications

For adhesive application on demanding substrates (concrete and metal surfaces) when modified bitumen or torch-applied modified bitumen membranes are used.

Instructions for use

Brush, roll or spray cleaned surfaces once with Kerabit KBL 20/100 modified bitumen solution. When necessary, dry the surfaces before treatment. The material need is 0,1 - 0,3 l/m². Let the modified bitumen solution fully dry before further treatment. Drying time about one hour at +20 °C. Clean the tools with white spirit or mineral spirit.

Handling and storage

In a closed container in a dry place protected from sunlight.

Kerabit

Prevention of environmental hazards

The product must be prevented from entering sewers, waterways or soil. Liquid waste must be transported to a waste collection point for hazardous waste, and empty, dry containers for recycling or, if this option is unavailable, to a public landfill.