Kerabit KBL 20/100

Päivitetty 25.4.2023 Tulostettu 12.11.2026



Kerabit KBL 20/100 Modified Bitumen Primer is a cold-applied, nicely spreading, quick-drying modified bitumen solution containing adhesion improving agents.

Kerabit KBL 20/100 forms an excellent underlay for an isolation layer made of Kerabit KB 100/50 modified bitumen or of torch-applied modified bitumen membranes. For adhesive application on demanding substrates (concrete and metal surfaces) when modified bitumen or torch-applied modified bitumen membranes are used. Mix before use.

The product is not for use indoors.

Technical data

Manufacturer / Manufactured for	Kerabit Oy, Lohja plant
Country of origin	Denmark
Drying time	2 - 3 hours at +20 °C
Need for materials	0,1 - 0,3 l / m²
Container Size	20 l

Additional information

Applications

For adhesive application on demanding substrates (concrete and metal surfaces) when modified bitumen or torch-applied modified bitumen membranes are used.

Instructions for use

Brush, roll or spray cleaned surfaces once with Kerabit KBL 20/100 modified bitumen solution. When necessary, dry the surfaces before treatment. The material need is 0,1 - 0,3 l/m². Let the modified bitumen solution fully dry before further treatment. Drying time about one hour at +20 °C. Clean the tools with white spirit or mineral spirit.

Handling and storage

In a closed container in a dry place protected from sunlight.

Prevention of environmental hazards

The product must be prevented from entering sewers, waterways or soil. Liquid waste must be transported to a waste collection point for hazardous waste, and empty, dry containers for recycling or, if this option is unavailable, to a public landfill.

This publication has been reviewed with the utmost care. However, we are not liable for any direct or indirect damages resulting from errors or the incorrect application of the information contained herein. We reserve the right to make changes. The latest version of this document is available at kerabit.fi/tuotteet.