

Kerabit

Kerabit 2400 UB

Päivitetty 25.4.2023 Tulostettu 23.5.2026

SBS modified bitumen membrane with reinforced polyester carrier. Sand granules on both side of the membrane. The under and top side 100 mm wide adhesive edges are on opposite sides.



Technical data

Manufacturer / Manufactured for	Kerabit Oy, Lohja plant
Country of origin	Finland
Conformity marking	CE mark
Reaction to fire	Manufacturer's fire testing certificate
Fire Classification	B _{ROOF} (t2)
Manufacturer's declaration of conformity	Kerabit modified bitumen roofing materials
Quality control	Quality control agreement between the Plant and Eurofins Expert Services Oy
Nominal thickness	2,2 mm
Nominal weight	2400 g/m ²
Weight of the supportive layer	150 g/m ² (+/- 5 g/m ²)
Supportive layer	reinforced polyester felt
Surface type	sand granules
Rolls size	1 x 10 m / 10 m ²
Packages / pallet	31 rolls
Weight / package	24 kg
Weight / pallet	769 kg

Additional information

Handling and storage

Modified bitumen membranes are to be stored on pallets in a dry and cool place. Use a plastic hood or tarpaulin for protection. When the outdoor temperature exceeds +40°C, the rolls must be protected from sunlight.

Applications

The product is used as underlay or intermediate layer of multi-layer roofing and underlay for bitumen shingles.

Checklist

→ Kerabit Sealing Adhesive for seaming gable seams